



tesa® 4962

Product Information



160 µm double sided translucent premium non woven tape

Product Features

- High initial tack and peel adhesion
- Excellent temperature resistance
- Very good bonding strength, even to low surface energy materials
- Outstanding converting and die-cutting properties
- Highly conformable to follow difficult 3D shapes due to non-woven backing

Product Description

tesa® 4962 is a double-sided non-woven industrial mounting and splicing tape with a highly tackified acrylic adhesive. The premium non-woven tape is, for instance, used for mounting signs and nameplates or other mounting and high performance lamination applications. tesa® 4962 is especially designed to connect flexible materials to one another. The mounting and splicing tape is able to withstand numerous environmental factors such as humidity, UV-light and temperatures of up to 200°C for limited periods of time. The tackified acrylic adhesive makes for an excellent hold on various surfaces, very high tack, and good shear strength. The adhesive is coated on a flexible and conformable cellulose non-woven backing which conforms even to difficult 3D shapes.

tesa® 4962 is also available in a 100µm version (tesa® 4959).

Application Fields

- tesa® 4962 is ideally used for industrial mounting, high performance lamination, and splicing applications
- Mounting of signs, covers, nameplates and door linings in the automotive industry
- Lamination of insulation materials and foams for HVAC (heating, ventilation, and air conditioning) seal
- Mounting of plastic bags, dispatch bags, continuous stationery, posters, etc.
- Splicing of paper and film webs

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|----------------------|---------------------|--------------------|-------------------|
| • Weight of liner | 80 g/m ² | • Color | translucent |
| • Color of liner | brown | • Backing material | non-woven |
| • Total thickness | 160 µm | • Type of adhesive | tackified acrylic |
| • Thickness of liner | 69 µm | • Type of liner | paper |

For latest information on this product please visit
<http://l.tesa.com/?ip=04962>



tesa® 4962

Product Information

Properties/Performance Values

• Elongation at break	3 %	• Temperature resistance short term	200 °C
• Static shear resistance at 23°C	good	• Tack	very good
• Chemical resistance	good	• Tensile strength	8 N/cm
• Static shear resistance at 40°C	medium	• Ageing resistance (UV)	very good
• Temperature resistance long term	80 °C	• Humidity resistance	very good

Adhesion to Values

• Steel (initial)	11.5 N/cm	• Aluminium (initial)	10 N/cm
• PE (initial)	6.5 N/cm	• ABS (after 14 days)	12 N/cm
• PC (after 14 days)	12.4 N/cm	• PC (initial)	13 N/cm
• PS (after 14 days)	13 N/cm	• PVC (initial)	11 N/cm
• ABS (initial)	11 N/cm	• PS (initial)	12 N/cm
• PP (after 14 days)	10 N/cm	• PET (initial)	9.5 N/cm
• PET (after 14 days)	10.5 N/cm	• PP (initial)	8.5 N/cm
• Aluminium (after 14 days)	10.5 N/cm	• Steel (after 14 days)	12 N/cm
• PE (after 14 days)	7 N/cm	• PVC (after 14 days)	15 N/cm
• PC (covered side, after 14 days)	14 N/cm		

Additional Information

According to VDA278 analysis, tesa® 4962 does not contain any single substances restricted by the drafted GB regulations (China) as well as the indoor concentration guideline by Health, Labour and Welfare Ministry (Japan).

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit
<http://l.tesa.com/?ip=04962>